



Hsin Sou Chemical Co., Ltd.

Office : 5F1-2, No.201 Fu Hsing N. Rd., Taipei Taiwan

Tel : 886-2-27139017

Kuan-Yin Fty : No.4, Ta-Tung 1ST RD., Kuan-Yin Industrial Park, Tao-yuan Tel : 886-3-4837778

CA-600

Carrier for high or low temp. dyeing

CA-600 is an excellent leveling agent for dyeing polyester and polyester blends at atmospheric temperatures or in pressure dyeing. It is suitable for all types of dyeing equipment including jet dyeing machines. Due to its excellent leveling and migrating properties, CA-600 is especially effective for eliminating barre effects and for repair of faulty dyeing.

General properties:

Appearance	:	Light yellow clear liquid
Composition	:	Phenyl derivatives compound
Ionic nature	:	Nonionic/anionic
pH (1% solution)	:	6.0 +/- 1.0
Solubility	:	Self emulsifiable in water to form a white emulsion

Special features:

1. Suitable for rapid dyeing procedures.
2. Excellent migration properties, minimizing barre effects.
3. Self-emulsifiable to form stable emulsion.
4. No residual odor on fabric with low toxicity.
5. Excellent color yield.
6. Low foaming properties.

Application:

Amount of product required depends on depth of shade and severity of barre condition.

1. For normal dyeing:

Dyes	X%(o.w.f)
SW-BSRN	1 ~ 2 g/l
CA-600	0.3 ~ 0.6 g/l
PA-60 CONC	0.5 ~ 1.0g/l
pH	5 ~ 5.5
Temp. xTime	110-130°C x30-60min

2. For eliminating barre effect:


dyes	X %
SW-BSRN	1 ~ 2 g/l
CA-600	0.6 ~ 1.2 g/l
PA-60 CONC	0.5 ~ 1.0g/l
pH	5 ~ 5.5
Temp. xTime	135°C x60min

3. For stripping :

CA-600	1.2 ~ 1.8 g/l
NaOH (45%) pH	9 ~ 12
Temp. xTime	130°C x45min

Reduction cleaning


80-90°C x20-25min



add HSINSOU K : 1.0 ~ 2.0g/l

NaOH(45%) : 1.0 ~ 2.0g/l

Acid neutralization



Note: full evaluation is recommended prior to commercial usage.